

SHADES OF PALE RAFFIA WEAVE ON NON-WOVEN BACKING



SOP1011

NB : The portrayed colours may differ from reality.

Reference SOP1011

Composition: raffia weave on non-woven backing

Weight: $\pm 529 \text{ g/m}^2$ ($\pm 15,43 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Light resistant:
Xeno test 6-7.



Ecological.




Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE ABACA AND SIMILI LEATHER WEAVE ON NON-WOVEN BACKING



SOP1021

NB : The portrayed colours may differ from reality.

Reference SOP1021

Composition: abaca and simili leather weave on non-woven backing

Weight: $\pm 972 \text{ g/m}^2$ ($\pm 28,35 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 3-4.



Ecological.



Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE BACNOC AND PAPER WEAVE ON NON-WOVEN BACKING



SOP1031

NB : The portrayed colours may differ from reality.

Reference SOP1031

Composition: bacnoc and paper weave on non-woven backing

Weight: $\pm 669 \text{ g/m}^2$ ($\pm 19,51 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 6-7.



Ecological.



Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE WEAVE OF TROPICAL LEAVES ON NON-WOVEN BACKING



SOP1041

NB : The portrayed colours may differ from reality.

Reference SOP1041

Composition: weave of tropical leaves on non-woven backing

Weight: $\pm 686 \text{ g/m}^2$ ($\pm 20,01 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 6-7.



Ecological.



Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE WATERLILY AND PAPER WEAVE ON NON-WOVEN BACKING



SOP1051

NB : The portrayed colours may differ from reality.

Reference SOP1051

Composition: waterlily and paper weave on non-woven backing

Weight: $\pm 536 \text{ g/m}^2$ ($\pm 15,63 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Light resistant:
Xeno test 4.



Ecological.



Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE CAPIZ WEAVE ON NON-WOVEN BACKING



SOP1061

NB : The portrayed colours may differ from reality.

Reference SOP1061

Composition: capiz on non-woven backing

Weight: $\pm 1220 \text{ g/m}^2$ ($\pm 35,58 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0") and
the design does
not need to be
matched.



Light resistant:
Xeno test 3-4.



Ecological.




Apply a ready
mixed PVA or
EVA clear
adhesive directly
to the wall.
Abundantly
humidify the
backing of the
wallcovering –
soaking time at
least 30 minutes



Sold by cut
length.

SHADES OF PALE CAPIZ WEAVE ON NON-WOVEN BACKING



SOP1062



SOP1063

NB : The portrayed colours may differ from reality.

References SOP1062, SOP1063

Composition: capiz on non-woven backing

Weight: $\pm 898 \text{ g/m}^2$ ($\pm 26,19 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0") and
the design does
not need to be
matched.



Light resistant:
Xeno test 5-6.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE LINEN ON NON-WOVEN BACKING



SOP2071



SOP 2074



SOP 2072



SOP 2073

NB : The portrayed colours may differ from reality.

References SOP207.

Composition: linen on non-woven backing

Weight: $\pm 401 \text{ g/m}^2$ ($\pm 11,7 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 129 \text{ cm}$ ($\pm 50'' \frac{4}{5}$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 5-7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.



Fire resistant:
EU: B, s1-d0

SHADES OF PALE CRUSHED LINEN ON NON-WOVEN BACKING



NB : The portrayed colours may differ from reality.

References SOP208.

Composition: crushed linen on non-woven backing

Weight: $\pm 285 \text{ g/m}^2$ ($\pm 8,31 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 110 \text{ cm}$ ($\pm 43'' \frac{3}{10}$).



Pattern repeat is
0 cm (0") and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.



Fire resistant:
EU: B, s1-d0



This design
requires reverse
hanging.

A delicate weave of linen yarns has been softly crushed to obtain a sophisticated yet natural look. A light stripe effect might occur after installation - this is part of the irresistible charm of this precious textile wallcovering.

SHADES OF PALE NON-WOVEN TEXTILE WALLCOVERING



NB : The portrayed colours may differ from reality.

References SOP310.

Composition: mixture of cellulose and polyester

Weight: $\pm 146 \text{ g/m}^2$ ($\pm 4,26 \text{ oz/sq yd}$)

Custom colouring on request.



Width of the wallcovering:
 $\pm 100 \text{ cm}$ ($\pm 39'' \frac{1}{3}$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Fire resistant:
EU: B, s1-d0
US: class A



Light resistant:
Xeno test 6.



This design
requires reverse
hanging.



Washable after
installation.



Breathable.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.



Manufactured
with recycled
fibres.



Printed with
solar energy.



Ecological.



The mark of
responsible forestry

SHADES OF PALE SISAL ON NON-WOVEN BACKING



SOP4101

NB : The portrayed colours may differ from reality.

Reference SOP4101

Composition: sisal on non-woven backing

Weight: $\pm 262 \text{ g/m}^2$ ($\pm 7,64 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35\frac{4}{5}$).



Pattern repeat is
0 cm (0") and
the design does
not need to be
matched.



Light resistant:
Xeno test 3-4.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly
to the wall.



Sold by cut
length.



This design
requires reverse
hanging.

SHADES OF PALE BAMBOO STRIPS ON NON-WOVEN BACKING



SOP4111

NB : The portrayed colours may differ from reality.

Reference SOP4111

Composition: bamboo strips on non-woven backing

Weight: $\pm 541 \text{ g/m}^2$ ($\pm 15,78 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE JUTE AND GRASS ON NON-WOVEN BACKING



SOP4121

NB : The portrayed colours may differ from reality.

Reference SOP4121

Composition: jute and grass on non-woven backing

Weight: $\pm 291 \text{ g/m}^2$ ($\pm 4,49 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.




Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE JUTE WEAVE ON NON-WOVEN BACKING



SOP4122

NB : The portrayed colours may differ from reality.

References SOP4122

Composition: jute weave on non-woven backing

Weight: $\pm 285 \text{ g/m}^2$ ($\pm 8,31 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE JUTE AND GRASS ON NON-WOVEN BACKING



SOP4123

NB : The portrayed colours may differ from reality.

Reference SOP4123

Composition: jute and grass on non-woven backing

Weight: $\pm 438 \text{ g/m}^2$ ($\pm 12,78 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE JUTE WEAVE ON NON-WOVEN BACKING



SOP4124

NB : The portrayed colours may differ from reality.

References SOP4124

Composition: jute weave on non-woven backing

Weight: $\pm 521 \text{ g/m}^2$ ($\pm 15,20 \text{ oz/sq yd}$)



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 7.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.

SHADES OF PALE LINEN ON NON-WOVEN BACKING



NB : The portrayed colours may differ from reality.

Reference SOP507.

Composition: linen on non-woven backing

Weight: $\pm 208 \text{ g/m}^2$ ($\pm 6,07 \text{ oz/sq yd}$)

The wallcovering can be installed vertically or horizontally.



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
 0 cm ($0''$) and
the design does
not need to be
matched.



Light resistant:
Xeno test 6.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.



This design
requires reverse
hanging.



Breathable.



Fire resistant:
EU: B, s1-d0
US: class A

SHADES OF PALE LINEN & VISCOSE ON NON-WOVEN BACKING



NB : The portrayed colours may differ from reality.

Reference SOP509.

Composition: linen & viscose warps on non-woven backing

Weight: $\pm 303 \text{ g/m}^2$ ($\pm 8,84 \text{ oz/sq yd}$)

The wallcovering can be installed vertically or horizontally.



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 6.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering.



Sold by cut
length.



This design
requires reverse
hanging.



Breathable.



Fire resistant:
EU: B, s1-d0
US: class A

SHADES OF PALE PAPER STRINGS ON NON-WOVEN BACKING



SOP5131



SOP5132



SOP5133

NB : The portrayed colours may differ from reality.

Reference SOP51..

Composition: 100% paperstrips on non-woven backing

Weight: $\pm 184 \text{ g/m}^2$ ($\pm 5,37 \text{ oz/sq yd}$)

The wallcovering can be installed vertically or horizontally.



Width of the wallcovering:
 $\pm 91 \text{ cm}$ ($\pm 35'' 4/5$).



Pattern repeat is
0 cm (0'') and
the design does
not need to be
matched.



Light resistant:
Xeno test 5-6.



Ecological.



Apply a ready
mixed PVA or
EVA clear adhesive
directly to the wall,
no need to humidify
the backing of the
wallcovering



Sold by cut
length.



This design
requires reverse
hanging.



Fire resistant:
EU: B, s1-d0
US: class A