

TECHNICAL SPECIFICATION



CONSTRUCTION

MACHINE GAUGE		5/32nd Loop Gauge
PILE HEIGHT	ISO 1766	5 mm
TUFT DENSITY	ISO 1763	89,279 Loops/m ²
PILE WEIGHT		1,017 gms/m ²
		30 oz/yd ²
TOTAL CARPET WEIGHT	ISO 8543	1,954 gms/m ²
CARPET THICKNESS	ISO 1765	7.9 mm
WIDTH		4 & 5 metre



COMPOSITION

PILE CONTENT	ISO 1833	100% Wool
PRIMARY BACKING		Woven Polypropylene
SECONDARY BACKING		Woven Secondary



PERFORMANCE

SUITABILITY		Extra Heavy Domestic / Medium Contract
WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 13,200 Rubs
STATIC LOADING	ISO 3416	28.6% Thickness loss after 24 hrs recovery
DYNAMIC LOADING	ISO 2094	26.5% Thickness loss after 1,000 impacts
TUFT ANCHORAGE	ISO 4919	Above 1 kg



COLOUR FASTNESS

LIGHT FASTNESS	ISO 105-B02	5/6 on all colours
WET FASTNESS	ISO 105-E01	4/5 on all colours
SHAMPOO FASTNESS	BS 1006:UK-TB	4/5 on all colours



THERMAL VALUE

TOG VALUE	ISO 5085-1	1.2 Tog
THERMAL RESISTANCE		0.12 m ² k/w



FLAMMABILITY

CE MARK RATING	CE	Cfl, S1
HOT METAL NUT TEST	BS4790	Pass - Low radius of ignition
METHENAMINE PILL TEST	ISO 6925	Pass



CHEMICAL IMPACT

FORMALDEHYDE	CE	E1
--------------	----	----



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT		Eulan Treated
-------------------------	--	---------------



ANTI STATIC

-0.3 kv (Requirement less than +2.0 kv)

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. Loop pile carpets should be vacuumed with a cylinder cleaner or suction head only. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less

frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Occasionally wool may contain traces of the sheep's natural environment. These traces can be easily removed and do not effect the durability of the carpet. Joins in loop pile carpet can sometimes be visible, especially so in patterned loop pile. The use of seaming cement is advisable.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.

Greenwood & Coope Ltd Brookhouse Mill, Greenmount, Bury, Lancashire, BL8 4HR
T: 01204 881234 | F: 01204 887722 | info@cormarcarpets.co.uk | www.cormarcarpets.co.uk

April 2019



NGC Nafees Wallpaper Co. LLC | PO Box 97035 | Dubai, UAE
Tel: 971 4 269 7272 | Email: sales@ngcmiddleeast.com

ngcmiddleeast.com