TECHNICAL SPECIFICATION LEVEL & STRIPE



CONSTRUCTION

MACHINE GAUGE PILE HEIGHT TUFT DENSITY PILE WEIGHT

ISO 1766 ISO 1763

ISO 8543

5/32nd Loop 79,360 tufts/m² 1,254 gms/m² 37 oz/yd² 2,191 gms/m²

5/32nd Loop 5 mm

4 & 5 metre

TEXTURED

79,360 tufts/m² 1,254 gms/m² 37 oz/yd² 2,191 gms/m² 7.9 mm

TOTAL CARPET WEIGHT CARPET THICKNESS WIDTH

ISO 1765

7.9 mm Level - 4 & 5 metre/Stripe - 4 metre

COMPOSITION PILE CONTENT ISO 1833 100% Pure New Wool PRIMARY BACKING Woven Polypropylene

100% Pure New Wool Woven Polypropylene Woven Secondary



PERFORMANCE

TUFT ANCHORAGE

SECONDARY BACKING

SUITABILITY WIRA ABRASION TEST STATIC LOADING DYNAMIC LOADING

PD 6527: Clause 17 ISO 3416 ISO 2094 ISO 4919

Extra Heavy Domestic/Medium Contact Exceeds 23,000 Rubs

15.4% Thickness Loss after 24 hrs recovery 20.0% Thickness Loss after 1,000 impacts

Extra Heavy Domestic / Medium Contract Exceeds 26,500 Rubs

20.5% Thickness loss after 24 hrs recovery 18% Thickness loss after 1,000 impacts



COLOUR FASTNESS

LIGHT FASTNESS WET FASTNESS SHAMPOO FASTNESS ISO 105-B02 ISO 105-E01 BS 1006: UK-TB 5 on all colours 4/5 on all colours 4/5 on all colours

Woven Secondary

5/6 on all colours 4/5 on all colours 4/5 on all colours



THERMAL VALUE

TOG VALUE THERMAL RESISTANCE ISO 5085-1

1.2 Tog $0.12 \, \text{m}^2 \, \text{k/w}$ 1.2 Tog 0.12 m² k/w



FLAMMABILITY

CE MARK RATING HOT METAL NUT TEST METHENAMINE PILL TEST

BS4790 ISO 6925

CE Cfl, S1

Pass - Low radius of ignition Pass

Cfl, S1 Pass - Low radius of ignition

Pass



CHEMICAL IMPACT

FORMALDEHYDE

CE

F1

F1



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT

Eulan Treated

Eulan Treated

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. Loop pile carpets should be vacuumed with a cylinder cleaner or suction head only. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear These areas will appear lighter or shaded in comparison to the less $frequent \textbf{I} \textbf{y} \ used \ parts. \ This \ shading \ / \ tracking \ or \ flattening$ happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Occasionally wool may contain traces of the sheep's natural environment. These traces can be easily removed and do not effect the durability of the carpet. Joins in loop pile carpet can sometimes be visible, especially so in patterned loop pile. The use of seaming cement is advisable.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.

Greenwood & Coope Ltd Brookhouse Mill, Greenmount, Bury, Lancashire, BL8 4HR T: 01204 881234 | F: 01204 887722 | info@cormarcarpets.co.uk | www.cormarcarpets.co.uk

April 2019

