

Technical Specification

	CONSTRUCTION		
	MACHINE GAUGE		1/10th Gauge
	PILE HEIGHT	ISO 1766	8.1 mm
	TUFT DENSITY	ISO 1763	162,749 tufts/m ²
	PILE WEIGHT		1,423 gms/m ² 42 oz/yd ²
	TOTAL CARPET WEIGHT	ISO 8543	2,360 gms/m ²
	CARPET THICKNESS	ISO 1765	11.2mm
	WIDTH		4 & 5 metre
	COMPOSITION		
	PILE CONTENT	ISO 1833	100% Excellon Polypropylene
	PRIMARY BACKING		Woven Polypropylene
	SECONDARY BACKING		Woven Secondary
	PERFORMANCE		
	SUITABILITY		Extra Heavy Domestic / Medium Contract
	WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 35,400 Rubs
	STATIC LOADING	ISO 3416	18.3% Thickness Loss after 24 hrs recovery
	DYNAMIC LOADING	ISO 2094	34.6% Thickness Loss after 1,000 impacts
	TUFT ANCHORAGE	ISO 4919	Above 1kg
	COLOUR FASTNESS		
	LIGHT FASTNESS	ISO 105-B02	6 on all colours
	WET FASTNESS	ISO 105-E01	5 on all colours
	SHAMPOO FASTNESS	ISO 18168	5 on all colours
	THERMAL VALUE		
	TOG VALUE	ISO 5085-1	1.2 Tog
	THERMAL RESISTANCE		0.12m ² k/w
	FLAMMABILITY		
	CE MARK RATING		Efl
	METHENAMINE PILL TEST	ISO 6925	Pass
	CHEMICAL IMPACT	CE	
	FORMALDEHYDE		E1
	BIOLOGICAL ATTACK		
	MOTH / INSECT RESISTANT		Insect & rot proof
	ANTI STATIC		0.0kv (Requirement less than +2.0kv)

General Information

INSTALLATION - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

MAINTENANCE - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

MATCHING - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

IMPORTANT - Minimum order length is 1.5 metres.

Greenwood & Coope Ltd

Brookhouse Mill, Greenmount, Bury, Greater Manchester, BL8 4HR
T: 01204 881234 | F: 01204 887722 | info@cormarcarpets.co.uk

www.cormarcarpets.co.uk

August 2021