

TECHNICAL PRODUCT SHEET (*Scheda Tecnica di prodotto*)

Article (<i>Articolo</i>)	<u>SUNRISE</u>
Thickness (<i>Spessore</i>)	1.4 – 1.6 mm
Raw Material (<i>Tipo di Pelle</i>)	<u>Bovine</u> (<i>bovino</i>)
Origin (<i>Provenienza</i>)	Italy
Average Size (<i>Taglia</i>)	18-20 Sq ft (Pq) Half hide
Tan Type (<i>Tipo Concia</i>)	Chrome Tanning (<i>Concia al Cromo</i>)
Finish Type (<i>Tipo Rifinitura</i>)	Pigmented (<i>Pigmentata</i>)
Embossing (<i>Stampa</i>)	With Emboss (<i>con stampa</i>)
Apparence (<i>Aspetto</i>)	Conform to the Master

PHYSICAL CHARACTERISTICS
Caratteristiche Fisiche

Rubbing test (UNI EN ISO 11640) <i>Solidità allo strofinio</i>	100 dry felt cycles (<i>cicli a secco</i>) ≥ 4/5 grey scale (<i>scala dei grigi</i>) 20 wet felt cycles (<i>cicli ad umido</i>) ≥ 4/5 grey scale (<i>scala dei grigi</i>)
Measurement of tensile strength (UNI EN ISO 5402-1) <i>Resistenza alla trazione</i>	Dry 20.000 cycles no cracks
Tear Resistance (UNI EN ISO 3377-1) <i>Resistenza allo strappo</i>	≥ 9.1 N
Dry abrasion resistance (UNI EN 13520: 2006) <i>Resistenza all'usura a secco</i>	Martindale method 15000 cycles ≥ 2 grey scale (<i>scala dei grigi</i>)
Dry rub 20 strokes crockmeter (Degradation) (UNI EN ISO 105 X12: 2003) Wet scrub 20 strokes crockmeter (Exhaust) (UNI EN ISO 105 X12: 2003)	≥ 5 grey scale (<i>scala dei grigi</i>) ≥ 5 grey scale (<i>scala dei grigi</i>)
Flammability	Cigarette Test Certification California Technical Bulletin 117:2013